

TRELLEBORG COATED SYSTEMS US, INC.
EXCELLENCE THROUGH INNOVATION

VX0303A00050
.050" Black Viton/Nomex

COATED FABRIC PROPERTIES	Test Method	REQUIREMENTS
Color	Visual	Black
Gauge	ASTM D 751-89, sec. 9	Range of 0.045 to 0.055 inches
Glued Adhesion	Fed. Std 191A, Method 5970	Minimum of 10.00 lbs/inch
Grab Tensile - Fill	ASTM D 751-89, sec. 11	Minimum of 450.00 lbf
Grab Tensile - Warp	ASTM D 751-89, sec. 11	Minimum of 450.00 lbf
Mullen Burst	ASTM D 751-89, sec. 18.3	Minimum of 750.00 psi
Mullen Burst	ASTM D 751-89, sec. 18.3	Minimum of 800.00 psi
Peel Adhesion	ASTM D 751-89, sec 43.1.1	Minimum of 5.00 lbs/inch
Total Weight	ASTM D 751-89, sec. 10.2	Record Only,
Volume Change	ASTM D 471	Maximum of 6.00 %
Width	ASTM D 751-89, sec. 8	37" useable

Original Date: 1/28/2015

The information supplied herein is based upon information currently available on the subject. It is offered as a possible helpful guide. Trelleborg Coated Systems US, Inc., makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING THE WARRANTY FOR FITNESS OF USE OR OF MERCHANTABILITY, UNLESS EXPRESSLY SET FORTH HEREIN.

TRELLEBORG COATED SYSTEMS US, INC.

715 Railroad Avenue

Rutherfordton, NC 28139

1-800-635-9350 - fax (828) 394-5005

