



Typical Data Sheet



PF-4S

**Pro-Formance[®]/MicroPore[®] Nonasbestos Gasket Material
F729000M9**

Description:

PF-4S is designed for various oil, air, and coolant applications such as oil pans, front covers, intake manifolds and rear seals. It is a replacement for styrene butadiene rubber bound asbestos and nonasbestos calendared sheet materials and offers improved oil sealability over nitrile butadiene bound materials. It is intended for applications with short duration maximum temperatures up to 290°C (550°F).

Property:	Specification:	Method:
Density, g/cc(lb/cu.ft)	1.44 (90) (min.)	ASTM F 1315
Compressibility, % (at 34.5MPa)	9 - 23	ASTM F 36
Recovery, %	45 (min.)	ASTM F 36
Tensile Strength, AMD, MPa(psi)	8.62 (1250) (min.)	ASTM F 152
Binder Type	Fully Cured Styrene Butadiene	

Remarks and Related Documents:

Specification values determined by the test methods required for ASTM F-104, Type 7 materials.

Hydro-Fused, MicroPore, Pro-Formance, Syntheseal, Thermo-Tork, Select-a-Seal and Voltoid are registered trademarks of Interface Solutions, Inc.

WARNING: The performance data provided herein represent typical values. This data sheet is not intended to be used as a purchase specification and does not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact Interface Sealing Solutions. INTERFACE SEALING SOLUTIONS EXPRESSLY DISCLAIMS ALL WARRANTIES EITHER EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT WILL ISI BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, CONSEQUENTIAL OR PUNITIVE DAMAGES, HOWEVER CAUSED AND ON ANY THEORY OF LIABILITY, WHETHER IN CONTRACT, STRICT LIABILITY, OR TORT (INCLUDING NEGLIGENCE OR OTHERWISE) ARISING IN ANY WAY OUT OF THE USE OF THE INFORMATION CONTAINED IN ITS SPECIFICATION DATA SHEETS, ITS PRODUCTS OR THEIR FUTURE USE BY YOU OR ANY OTHER PERSON OR ENTITY.

North American Sales Office:

Interface Sealing Solutions,
22260 Haggerty Road, Suite 200
Northville, MI 48167

Tel: (248) 596-2800
Fax: (248) 596-2880

Corporate Headquarters

Interface Sealing Solutions
410 South First Avenue
Marshalltown, IA 50158
Toll-free: 1-877-9GASKET
Tel: 641-752-6736
Fax: 641-752-7476

[HTTP://WWW.INTERFACSEALINGSOLUTIONS.COM](http://WWW.INTERFACSEALINGSOLUTIONS.COM)

Previous Revision Date: 12-14-2005
Latest Revision Date: 01-04-2006

© 2015 INTERFACE SEALING SOLUTIONS | Phone: 1-877-9GASKET | [PRIVACY POLICY](#) | [SITE MAP](#)

[close window](#)