

TRELLEBORG COATED SYSTEMS US, INC.**07192****EXCELLENCE THROUGH INNOVATION****.062" Black Nitrile/Nylon**

COATED FABRIC PROPERTIES	Test Method	REQUIREMENTS
Color	Visual	Black
Gauge	ASTM D 751-89, sec. 9	Range of 0.057 to 0.067 inches
Glued Adhesion	Fed. Std 191A, Method 5970	Minimum of 10.00 lbs/inch
Mullen Burst	ASTM D 751-89, sec. 18.3	Minimum of 800.00 psi
Strip Tensile - Fill	ASTM D 751-89, sec. 16	Minimum of 300.00 lbs
Strip Tensile - Warp	ASTM D 751-89, sec. 16	Minimum of 350.00 lbs
Thickness Change	ASTM D 471-79, sec. 11	Maximum of 100.00 %
Width	ASTM D 751-89, sec. 8	60" Trimmed

Original Date: 5/15/2015

The information supplied herein is based upon information currently available on the subject. It is offered as a possible helpful guide. Trelleborg Coated Systems US, Inc., makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING THE WARRANTY FOR FITNESS OF USE OR OF MERCHANTABILITY, UNLESS EXPRESSLY SET FORTH HEREIN.

TRELLEBORG COATED SYSTEMS US, INC.

715 Railroad Avenue

Rutherfordton, NC 28139

1-800-635-9350 - fax (828) 394-5005

