

COATED FABRIC PROPERTIES	Test Method	REQUIREMENTS
Color	Visual	Black
Copper wire test	Trelleborg Test Method	Record Only,
DuPont Scrubs	Trelleborg Test Method	Pass
Gauge	ASTM D 751-89, sec. 9	Range of 0.022 to 0.028 inches
Grab Tensile - Fill	ASTM D 751-89, sec. 11	Minimum of 250.00 lbs/inch
Grab Tensile - Warp	ASTM D 751-89, sec. 11	Minimum of 250.00 lbs/inch
Mullen Burst	ASTM D 751-89, sec. 18.3	Minimum of 475.00 psi
Peel Adhesion	ASTM D 751-89, sec 43.1.1	Minimum of 4.00 lbs/inch
State of Cure	Trelleborg Test Method	Pass
Thickness Change	ASTM D 471-79, sec. 11	Maximum of 120.00 %
Weight	ASTM D 751-89, sec. 10.2	25.10 Nominal oz/sq yd
Width	ASTM D 751-89, sec. 8	57" Untrimmed

Original Date: 5/18/2015

The information supplied herein is based upon information currently available on the subject. It is offered as a possible helpful guide. Trelleborg Coated Systems US, Inc., makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING THE WARRANTY FOR FITNESS OF USE OR OF MERCHANTABILITY, UNLESS EXPRESSLY SET FORTH HEREIN.

TRELLEBORG COATED SYSTEMS US, INC.

715 Railroad Avenue

Rutherfordton, NC 28139

1-800-635-9350 - fax (828) 394-5005

