

TRELLEBORG COATED SYSTEMS US, INC.
EXCELLENCE THROUGH INNOVATION

VG0001000010
.010" Black FKM/Fiberglass

COATED FABRIC PROPERTIES	Test Method	REQUIREMENTS
Color	Visual	Black
Curl test	Trelleborg Test Method	Maximum of 0.16 inches
Gauge	ASTM D 751-89, sec. 9	Range of 0.009 to 0.012 inches
Grab Tensile - Fill	ASTM D 751-89, sec. 11	Minimum of 60.00 lbf
Grab Tensile - Warp	ASTM D 751-89, sec. 11	Minimum of 60.00 lbf
Mullen Burst	ASTM D 751-89, sec. 18.3	Minimum of 200.00 psi
Peel Adhesion	ASTM D 751-89, sec 43.1.1	Minimum of 4.00 lbs/inch
Permeation		Pass
Toluene Immersion		Pass
Width	ASTM D 751-89, sec. 8	36" Untrimmed

Original Date: 5/18/2015

The information supplied herein is based upon information currently available on the subject. It is offered as a possible helpful guide. Trelleborg Coated Systems US, Inc., makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING THE WARRANTY FOR FITNESS OF USE OR OF MERCHANTABILITY, UNLESS EXPRESSLY SET FORTH HEREIN.

TRELLEBORG COATED SYSTEMS US, INC.

715 Railroad Avenue

Rutherfordton, NC 28139

1-800-635-9350 - fax (828) 394-5005

