

TRELLEBORG COATED SYSTEMS US, INC.**VS006000031****EXCELLENCE THROUGH INNOVATION****.031" Black FKM Rubber Gum**

COATED FABRIC PROPERTIES	Test Method	REQUIREMENTS
Color	Visual	Black
Elongation	ASTM D 412, Method A	Minimum of 200.00 %
Gauge	ASTM D 751-89, sec. 9	Range of 0.028 to 0.034 inches
Shore A Hardness	ASTM D 2240 - 91	Range of 55.00 to 65.00
Tensile	ASTM D 412, Method A	Minimum of 1,000.00 psi
Weight	ASTM D 751-89, sec. 10.2	Record Only,
Width	ASTM D 751-89, sec. 8	37" Trimmed

Original Date: 4/7/2015

The information supplied herein is based upon information currently available on the subject. It is offered as a possible helpful guide. Trelleborg Coated Systems US, Inc., makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING THE WARRANTY FOR FITNESS OF USE OR OF MERCHANTABILITY, UNLESS EXPRESSLY SET FORTH HEREIN.

TRELLEBORG COATED SYSTEMS US, INC.

715 Railroad Avenue

Rutherfordton, NC 28139

1-800-635-9350 - fax (828) 394-5005

