

COATED FABRIC PROPERTIES	Test Method	REQUIREMENTS
Color	Visual	Black
Elongation	ASTM D 412, Method A	Minimum of 150.00 %
Gauge	ASTM D 751-89, sec. 9	Range of 0.028 to 0.034 inches
Shore A Hardness	ASTM D 2240 - 91	Range of 75.00 to 85.00
Tensile	ASTM D 412, Method A	Minimum of 1,200.00 psi
Volume Change	ASTM D 471	Range of 10.30 to 20.30 %
Width	ASTM D 751-89, sec. 8	37" +/- 1/2"

Original Date: 7/19/2012

The information supplied herein is based upon information currently available on the subject. It is offered as a possible helpful guide. Trelleborg Coated Systems US, Inc., makes no guarantee of results and assume