

COATED FABRIC PROPERTIES	Test Method	REQUIREMENTS
Color	Visual	Black
Curl test	Trelleborg Test Method	Record Only, inches
Gauge	ASTM D 751-89, sec. 9	Range of 0.020 to 0.030 inches
Mullen Burst	ASTM D 751-89, sec. 18.3	Minimum of 300.00 psi
Mullen Hydrostatic	ASTM D 751-89, sec. 34.2	Minimum of 200.00 psi
Peel Adhesion	ASTM D 751-89, sec 43.1.1	Minimum of 3.00 lbs/inch
Strip Tensile - Fill	ASTM D 751-89, sec. 16	Minimum of 70.00 lbf
Strip Tensile - Warp	ASTM D 751-89, sec. 16	Minimum of 100.00 lbf
Toluene Immersion		Pass
Tongue Tear - Fill	ASTM D 751-89, sec. 29	Minimum of 3.00 lbf
Tongue Tear - Warp	ASTM D 751-89, sec. 29	Minimum of 3.00 lbf
Width	ASTM D 751-89, sec. 8	36" Minimum Untrimmed

Original Date: 5/18/2015

The information supplied herein is based upon information currently available on the subject. It is offered as a possible helpful guide. Trelleborg Coated Systems US, Inc., makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING THE WARRANTY FOR FITNESS OF USE OR OF MERCHANTABILITY, UNLESS EXPRESSLY SET FORTH HEREIN.

TRELLEBORG COATED SYSTEMS US, INC.

715 Railroad Avenue

Rutherfordton, NC 28139

1-800-635-9350 - fax (828) 394-5005

