

TRELLEBORG COATED SYSTEMS US, INC.**VX0003000032****EXCELLENCE THROUGH INNOVATION****.032" Black Anti-wicking Viton/Nomex**

COATED FABRIC PROPERTIES	Test Method	REQUIREMENTS
Color	Visual	Black
Gauge	ASTM D 751-89, sec. 9	Range of 0.029 to 0.035 inches
Grab Tensile - Fill	ASTM D 751-89, sec. 11	Minimum of 75.00 lbf
Grab Tensile - Warp	ASTM D 751-89, sec. 11	Minimum of 75.00 lbf
Small Jig Antiwicking	Trelleborg Test Method	Pass
Mullen Burst	ASTM D 751-89, sec. 18.3	Minimum of 160.00 psi
Peel Adhesion	ASTM D 751-89, sec 43.1.1	Minimum of 7.00 lbs/inch
Width	ASTM D 751-89, sec. 8	50" Minimum Trimmed

Original Date: 5/18/2015

The information supplied herein is based upon information currently available on the subject. It is offered as a possible helpful guide. Trelleborg Coated Systems US, Inc., makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING THE WARRANTY FOR FITNESS OF USE OR OF MERCHANTABILITY, UNLESS EXPRESSLY SET FORTH HEREIN.

TRELLEBORG COATED SYSTEMS US, INC.

715 Railroad Avenue

Rutherfordton, NC 28139

1-800-635-9350 - fax (828) 394-5005

