

Typical Data Sheet



EMC-7201

EnCore®Combined Materials

Description:

EMC-7201 is a composite structure of high-density, fully cured nitrile butadiene bound gasket facings chemically and mechanically fused to an expanded steel core. Typical applications include diesel engine structural joints such as gear case or flywheel housings, high pressure hydraulic joints, and performance and racing engine applications. It is available in 0.030, 0.042, and 0.060 inch gauges in a sheet size of 21 by 63 inches (usable area).

Property: Specification: Method:

Caliper, mm(inch)	1.1 (0.042)	ASTM F 104
Density, g/cc(lb/cu.ft)	2.20 (137)	ASTM F 1315
Compressibility, % (at 34.5MPa)	14	ASTM F 36
Recovery, %	50	ASTM F 36
Tensile Strength, AMD, MPa(psi)	37.90 (5500)	ASTM F 152
Tensile Strength, MD, MPa(psi)	15.20 (2200)	ASTM F 152
Fluid Resistance, IRM903 Oil	•	ASTM F 146
Change in Thickness, %	3	
Fluid Resistance, Glycol/Water 50/5	0	ASTM F 146
Change in Thickness, %	6	
Binder Type	Fully Cured Nitrile Butadiene	
Color	Dark Grey	

Remarks and Related Documents:

Specification values determined by the test methods required for ASTM F-104, Type 7 materials.

Hydro-Fused, MicroPore, Pro-Formance, Syntheseal, Thermo-Tork, Select-a-Seal and Voltoid are registered trademarks of Interface Solutions, Inc.

WARNING: The performance data provided herein represent typical values. This data sheet is not intended to be used as a purchase specification and does not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact Interface Sealing Solutions. INTERFACE SEALING SOLUTIONS EXPRESSLY DISCLAIMS ALL WARRANTIES EITHER EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT WILL ISI BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, CONSEQUENTIAL OR PUNITIVE DAMAGES, HOWEVER CAUSED AND ON ANY THEORY OF LIABILITY, WHETHER IN CONTRACT, STRICT LIABILITY, OR TORT (INCLUDING NEGLIGENCE OR OTHERWISE) ARISING IN ANY WAY OUT OF THE USE OF THE INFORMATION CONTAINED IN ITS SPECIFICATION DATA SHEETS, ITS PRODUCTS OR THEIR FUTURE USE BY YOU OR ANY OTHER PERSON OR ENTITY.

Tel: (248) 596-2800

Fax: (248) 596-2880

North American Sales Office:

Corporate Headquarters

Interface Sealing Solutions 410 South First Avenue Marshalltown, IA 50158 Toll-free: 1-877-9GASKET Tel: 641-752-6736 Fax: 641-752-7476

HTTP://WWW.INTERFACESEALINGSOLUTIONS.COM

Previous Revision Date: 07-10-2013 Latest Revision Date: 07-11-2013

© 2015 INTERFACE SEALING SOLUTIONS | Phone: 1-877-9GASKET | PRIVACY POLICY | SITE MAP

close window