3M

High Strength Double Coated Tape with Adhesive 300LSE

93010LE • 93015LE • 93020LE

Technical Data January, 2011

Product Description

3M TM Double Coated Tapes with 3MTM Adhesive 300LSE provides high bond strength to most surfaces, including many low surface energy plastics such as polypropylene and powder coated paints. The acrylic adhesive also provides excellent adhesion to surfaces contaminated with oil typically used with machine parts.

Construction Information

Product Number	Faceside ¹ Adhesive Type Thickness	Carrier Type Thickness	Backside ² Adhesive Type Thickness	Liner Color, Type, Caliper ³	Total Thickness (w/o liner)
3M [™] Double Coated Tape 93010LE	300LSE 0.044 mm (1.7 mil)	Clear Polyester 0.012 mm (0.5 mil)	300LSE 0.044 mm (1.7 mil)	Tan, 58# Polycoated Kraft 0.11 mm (4.2 mil)	0.10 mm (3.9 mil)
3M [™] Double Coated Tape 93015LE	300LSE 0.069 mm (2.7 mil)	Clear Polyester 0.012 mm (0.5 mil)	300LSE 0.069 mm (2.7 mil)	Tan, 58# Polycoated Kraft 0.11 mm (4.2 mil)	0.15 mm (5.9 mil)
3M [™] Double Coated Tape 93020LE	300LSE 0.095 mm (3.7 mil)	Clear Polyester 0.012 mm (0.5 mil)	300LSE 0.095 mm (3.7 mil)	Tan, 58# Polycoated Kraft 0.11 mm (4.2 mil)	0.20 mm (7.9 mil)

Note 1: Faceside (FS) adhesive is on the interior of the roll, exposed when unwound.

Note 2: Backside (BS) adhesive is on the exterior of the roll, exposed when liner is removed.

Note 3: The caliper listed is based on a calculation from manufacturing controlled adhesive coat weights using a density of 1.012 g/cc.

3M™ High Strength Double Coated Tape with Adhesive 300LSE

93010LE • 93015LE • 93020LE

Typical Physical Properties and Performance Characteristics Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

					3МТ	™ Dou	ble Co	ated Tape				
Product Number		93010LE			93015LE			93020LE				
Adhesive		300LSE			300LSE			300LSE				
Tape Thickness		0.10 mm			0.15 mm			0.20 mm				
Breakdown Voltage		5600 volts			6900 volts			7500 volts				
Dielectric Strength	1400 volts/mil		1200 volts/mil			900 volts/mil						
Adhesion 15 min dwell @ RT Modified ASTM D-3330 180 degree peel 2 mil Al foil backing	SS PC ABS PP	oz/in 85 110 80 95	N/cm 9.3 12.3 8.8 10.4	kg/25.4mm 2.4 3.1 2.3 2.7	SS PC ABS PP	oz/in 100 130 85 105	N/cm 10.9 14.2 9.3 11.5	kg/25.4mm 2.8 3.7 2.4 3.0	SS PC ABS PP	oz/in 155 165 145 155	N/cm 17.0 18.1 15.9 17.0	kg/25.4mm 4.4 4.7 4.1 4.4
Adhesion 72 hr dwell @ RT Modified ASTM D-3330 180 degree peel 2 mil Al foil backing	SS PC ABS PP	oz/in 110 140 110 110	N/cm 12.0 15.3 12.0 12.0	kg/25.4mm 3.1 4.0 3.1 3.1	SS PC ABS PP	oz/in 125 165 125 135	N/cm 13.7 18.1 13.7 14.8	kg/25.4mm 3.6 4.7 3.6 3.9	SS PC ABS PP	oz/in 170 180 155 175	N/cm 18.6 19.7 17.0 19.2	kg/25.4mm 4.8 5.1 4.4 5.1
Shear Strength at RT Modified ASTM D-3654 1 inch² sample size 1000 grams		10,000 Minutes			10,000 Minutes			10,000 Minutes				
Shear Strength at 158°F (70°C) Modified ASTM D-3654 1 inch² sample size 500 grams 10,000 Minutes		10,000 Minutes		10,000 Minutes								

Features

- This tape has a film carrier which can add dimensional stability to foams and other substrates and also makes it easier to handle the tape during slitting and diecutting.
- The bond strength of 3MTM Adhesive 300LSE increases as a function of time and temperature, and has very high initial adhesion.

Available Sizes

Roll length, width, slitting tolerance, core size.

Product	3M [™] Double Coated Tape 93010LE • 93015LE • 93020LE				
Maximum Length in.:					
1/2" to 63/64"	180 yds. (164 m)				
1" to 3"	360 yds. (329 m)				
3" to 48"	360 yds. (329 m)				
48" to 54"	360 yds. (329 m)				
Normal Slitting Tolerance:	± 1/32 in. (0.08 mm)				
Core Size (ID):	3.0 in. (76.2 mm)				

3M[™] High Strength Double Coated Tape with Adhesive 300LSE

93010LE • 93015LE • 93020LE

Temperature	Long Term (days, weeks):	250°F (121°C)
Resistance	Short Term (minutes, hours):	300°F (149°C)

U.V. Resistance

Humidity Resistance

Adhesive is resistant to oxidation and ozone when exposed to air or ultraviolet light.

No adverse effect on the bond after exposed to 100% relative humidity at 100°F (38°C).

Application Techniques

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improve bond strength. To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Some typical surface cleaning solvents are isopropyl alcohol or heptane.*

*Note: Carefully read and follow the manufacturer's precautions and directions for use when using solvents. Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

Environmental Performance

Humidity Resistance: High humidity has minimal effect on adhesive performance. No significant reduction in bond strength is observed after exposure for 7 days at 90°F (32°C) and 90% relative humidity.

UV Resistance: When properly applied, nameplates and decorative trim parts are not adversely affected by exposure.

Water Resistance: Immersion in water has no appreciable effect on the bond strength. After 100 hours at room temperature, the high bond strength is maintained.

Temperature Cycling Resistance: High bond strength is maintained after cycling four times through:

- 4 hours at 158°F (70°C)
- 4 hours at -20°F (-29°C)
- 4 hours at 73°F (22°C)

Chemical Resistance: When properly applied, nameplate and decorative trim parts will hold securely after exposure to numerous chemicals including oil, mild acids, and alkalis.

Application Ideas

- Foam to powder coated painted surfaces.
- Low surface energy plastic adhesion.

3M™ High Strength Double Coated Tape with Adhesive 300LSE

93010LE • 93015LE • 93020LE

Storage	Store in original cartons at 70°F (21°C) and 50% relative humidity.
Shelf Life	If stored under proper conditions, these products retain their performance and properties for two years from date of manufacture.
Technical Information	The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.
Product Use	Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.
Warranty, Limited Remedy, and Disclaimer	Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2008 standards.



Industrial Adhesives and Tapes Division Converter Markets

3M Center, Building 225-3S-06 St. Paul, MN 55144-1000 800-223-7427 • 651-778-4244 (fax) www.3M.com/converter

