

# **Specification Data Sheet**



## N-8051

Standard/Nonasbestos Gasket Material F339000M9, Z1

#### Description:

N-8051 is a light-duty material for low internal pressure and low flange pressure applications up to 13.8 MPa (2000 psi). It has a nitrile butadiene rubber binder for resistance to oil and is intended for applications with short duration maximum temperatures up to  $180^{\circ}\text{C}$  (350°F).

Property: Specification: Method:

Compressibility, % (at 2.8MPa)	10 - 25	ASTM F 36
Recovery, %	40 (min.)	ASTM F 36
Tensile Strength, AMD, MPa(psi)	2.76 (400) (min.)	ASTM F 152
Fluid Resistance, IRM901 Oil	, , ,	ASTM F 146
Change in Volume, %	35 (max.)	
Fluid Resistance, Fuel A		ASTM F 146
Change in Volume, %	45 (max.)	
Binder Type	Nitrile Butadiene	

#### **Remarks and Related Documents:**

Specification values determined by the test methods required for ASTM F-104, Type 2 materials.

EnCore, Hydro-Fused, Pro-Formance, Select-a-Seal, Syntheseal, Thermo-Tork, and Voltoid are registered trademarks of Interface Solutions, Inc. MicroPore is a trademark of Interface Solutions, Inc.

WARNING: The description and performance data provided herein constitute a material specification for quality control purposes, but do not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact Interface Solutions. INTERFACE SOLUTIONS EXPRESSLY DISCLAIMS ALL WARRANTIES EITHER EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT WILL ISI BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, CONSEQUENTIAL OR PUNITIVE DAMAGES, HOWEVER CAUSED AND ON ANY THEORY OF LIABILITY, WHETHER IN CONTRACT, STRICT LIABILITY, OR TORT (INCLUDING NEGLIGENCE OR OTHERWISE) ARISING IN ANY WAY OUT OF THE USE OF THE INFORMATION CONTAINED IN ITS SPECIFICATION DATA SHEETS, ITS PRODUCTS OR THEIR FUTURE USE BY YOU OR ANY THIRD PARTIES, EVEN IF ADVISED OF THE POSSIBILITY OF SUCH DAMAGE.

#### North American Sales Office:

Interface Sealing Solutions 22260 Haggerty Road , Suite 200 Northville, MI 48167 Tel: (248) 596-2800 Fax: (248) 596-2880

#### **Corporate Headquarters**

Interface Solutions, Inc. 216 Wohlsen Way Lancaster, PA 17603-4043 717-207-6000

### HTTP://WWW.SEALINFO.COM

Previous Revision Date: 07-10-2013 Latest Revision Date: 07-11-2013

© 2015 INTERFACE SEALING SOLUTIONS | Phone: 1-877-9GASKET | PRIVACY POLICY | SITE MAP

close window