

- Products
- Service and Support
- About Us
- Where to Buy
- Contact Us

## S-8091

Home

[PRINT THIS PAGE](#)  
[PDF VERSION](#)

### Specification Data Sheet

## S-8091

Syntheseal®/Nonasbestos Gasket Material  
 F724900E09M9

#### Description:

S-8091 is controlled-swell, Latent cure styrene butadiene bound material with reinforced cellulose fiber. It is intended for applications sealing oil, fuel, and low-pressure steam with short duration maximum temperatures up to 180°C (350°F).

Property:	Specification:	Method:
Density, g/cc(lb/cu.ft)	1.20 (75) (min.)	ASTM F 1315
Compressibility, % (at 34.5MPa)	15 - 25	ASTM F 36
Recovery, %	25 (min.)	ASTM F 36
Tensile Strength, AMD, MPa(psi)	12.41 (1800) (min.)	ASTM F 152
Fluid Resistance, IRM903 Oil		ASTM F 146
Change in Thickness, %	30 - 75	
Fluid Resistance, Fuel B		ASTM F 146
Change in Thickness, %	25 - 50	
Binder Type	Styrene Butadiene	

#### Remarks and Related Documents:

Specification values determined by the test methods required for ASTM F-104, Type 7 materials.

EnCore, Hydro-Fused, MicroPore, Pro-Formance, Select-a-Seal, Syntheseal, Thermo-Tork, and Voltoid are registered trademarks of Interface Solutions, Inc. Select-a-Shield is a trademark of Interface Solutions, Inc.

WARNING: The description and performance data provided herein constitute a material specification for quality control purposes, but do not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact Interface Solutions. INTERFACE SOLUTIONS EXPRESSLY DISCLAIMS ALL WARRANTIES EITHER EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT WILL ISI BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, CONSEQUENTIAL OR PUNITIVE DAMAGES, HOWEVER CAUSED AND ON ANY THEORY OF LIABILITY, WHETHER IN CONTRACT, STRICT LIABILITY, OR TORT (INCLUDING NEGLIGENCE OR OTHERWISE) ARISING IN ANY WAY OUT OF THE USE OF THE INFORMATION CONTAINED IN ITS SPECIFICATION DATA SHEETS, ITS PRODUCTS OR THEIR FUTURE USE BY YOU OR ANY THIRD PARTIES, EVEN IF ADVISED OF THE POSSIBILITY OF SUCH DAMAGE.

#### Customer Service Contacts:

North America, Interface Solutions, Inc.  
 22260 Haggerty Road, Suite 200  
 Northville, MI 48167 USA

Tel: 800 9GASKET ( 800-942-7538)  
 Tel: (Outside USA) 1-248-596-2800  
 Fax: 248-596-2880

Korea, Interface Solutions  
 Room 406, Office Line, #401 Green Plaza., 19-2  
 Soonae-Dong, Boondang-Gu, Seongnam-City, Kyunggi-Do  
 South Korea, 463-825

Tel: +82-31-716-1923  
 Fax: +82-31-716-7235

Europe, Interface Sealing Solutions Europe  
 Lili Pean, Le Bourg, 64240 Bonloc, France

Tel: +33 (0) 5 59 29 12 20  
 Fax: +33 (0) 5 59 29 18 85

#### Corporate Headquarters

Interface Solutions, Inc.  
216 Wohlsen Way  
Lancaster, PA 17603-4043  
717-207-6000  
[HTTP://WWW.SEALINFO.COM](http://www.sealinfo.com)

*Previous Revision Date: 07-02-2008*

*Latest Revision Date: 07-02-2008*

[▲ BACK TO TOP](#)