



BKJN400 Typical OleTex Foam Properties

Standard Test	ASTM D-3575	BKJN400
Density, lb/cu ft	Suffix W	4.0
Tensile Strength, PSI	Suffix T	118
Elongation, %	Suffix T	290
Tear Resistance	Suffix G	20.0
Compression Strength, psi	Suffix D	
10% Deflection		17.0
25% Deflection		20.0
40% Deflection		25.0
50% Deflection		31.0
Compression Set, %	Suffix B	9.5
Thermal Stability, % Change (24 hours @ 158° F)	Suffix S	< 2

Properties are averages of machine and cross direction

For updates to this document please refer to our website.

Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information is provided as a technical service, and the data and information are subject to change without notice.

Armacell LLC • 16800 South Canal Street • South Holland, IL 60473
email: info.us@armacell.com • www.armacell.com

South Holland, IL • 800-343-1255 • fax: 708-596-9270

© 2007 Armacell LLC

BKJN400	01	06	07	NA	NA
---------	----	----	----	----	----

OleTex® is a registered trademark of Armacell

ALL ARMACELL FACILITIES IN NORTH AMERICA ARE
ISO 9001:2000 OR ISO/TS 16949:2002 CERTIFIED