

COATED FABRIC PROPERTIES	TEST METHOD	REQUIREMENTS
Color	Visual	Black
Width (trimmed)	ASTM D 751-89, sec. 8	60"
Gauge	ASTM D 751-89, sec. 9	0.031" +/- 0.003"
Peel Adhesion - Side 1	ASTM D 751-89, sec. 43.1.1	5.0 lb/in. min.
Peel Adhesion - Side 2	ASTM D 751-89, sec. 43.1.1	5.0 lb/in. min.
Mullen Burst	ASTM D 751-89, sec. 18.3	700 psi min.

The EPDM compound utilized for this specification is made only from chemicals listed in and complying with requirements of Federal Regulation Title 21, Chapter 177.2600, para. © (4).

Original Date: 11/03/2014

The information supplied herein is based upon information currently available on the subject. It is offered as a possible helpful guide. TCS, Inc., makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING THE WARRANTY FOR FITNESS OF USE OR OF MERCHANTABILITY, UNLESS EXPRESSLY SET FORTH HEREIN.

TRELLEBORG COATED SYSTEMS US, INC.
 715 Railroad Ave
 Rutherfordton, NC 28139
 1-800-635-9350

