

COATED FABRIC PROPERTIES	Test Method	REQUIREMENTS
Color	Visual	Black
Cold crack	ASTM D 2136-84 Sec.8	Pass
Curl test	Trelleborg Test Method	Maximum of 0.25 inches
DuPont Scrubs	Trelleborg Test Method	Pass
Gauge	ASTM D 751-89, sec. 9	Range of 0.008 to 0.012 inches
Grab Tensile - Fill	ASTM D 751-89, sec. 11	Minimum of 60.00 lbs/inch
Grab Tensile - Warp	ASTM D 751-89, sec. 11	Minimum of 65.00 lbs/inch
Mullen Burst	ASTM D 751-89, sec. 18.3	Minimum of 135.00 psi
Peel Adhesion	ASTM D 751-89, sec 43.1.1	Minimum of 3.00 lbs/inch
Shore A Durometer	ASTM D 2240-91	Record Only,
Thickness Change	ASTM D 471-79, sec. 11	Maximum of 115.00 %
Total Weight	ASTM D 751-89, sec. 10.2	7.80 Nominal
Width	ASTM D 751-89, sec. 8	55" useable untrimmed

Original Date: 2/26/2015

The information supplied herein is based upon information currently available on the subject. It is offered as a possible helpful guide. Trelleborg Coated Systems US, Inc., makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING THE WARRANTY FOR FITNESS OF USE OR OF MERCHANTABILITY, UNLESS EXPRESSLY SET FORTH HEREIN.

TRELLEBORG COATED SYSTEMS US, INC.

715 Railroad Avenue

Rutherfordton, NC 28139

1-800-635-9350 - fax (828) 394-5005

