

RG-SI40

Thermoseal RG-SI40 is a controlled-swell gasket material that provides excellent sealing where initial gasket conformability is required to compensate for flange out of flatness or roughness. After establishing initial sealability, the styrene butadiene binder fully vulcanizes with time and heat of component operation to provide long lasting performance. RG-SI40 contains a unique blend of aramid, mineral, and cellulose fibers as well as mineral fillers to provide enhanced crush and temperature resistance. A factory applied release coating on both sides aids in flange removal. Continuous roll lengths allow efficient and economical fabrication with high speed die cutting equipment. Typical applications include gaskets for sealing hot oil or coolant in machinery including small engines and automotive and heavy duty diesel engines with intermittent operating temperatures up to 550° F (288° C).



| | |
|--|--|
| Ref. Thickness of Measured Values | 0.031" (0.8mm) |
| Density ASTM F1315 | 87 lbs/ft ³ (1.40 g/cm ³) |
| Compressibility ASTM F36J | 12 - 25% |
| Recovery ASTM F36J | minimum 35% |
| Tensile Strength ASTM F152 | minimum 870 psi (6 MP _a) |
| Fluid Resistance | |
| After immersion in Oil IRM903 | |
| Weight increase | maximum 45% |
| Thickness Increase | maximum 60% |
| Binder Type | Styrene Butadiene Rubber (Partially Vulcanized) |
| ASTM F104 Line Call Out | F729900E09M9 |

For Additional Information Call Toll Free 1.800.990.7325 or email info@thermosealinc.com.

Thermoseal Inc. 2350 Campbell Rd., Sidney, Ohio 45365 United States, Tel: (937) 498-2222, Fax: (937) 498-4911
www.thermosealinc.com, email: info@thermosealinc.com
